



## GI 225

### Flexible coating

- Crack-bridging
- Lightfast
- Glossy
- Pigmented

<b>Product description:</b>	GI 225 is a solvent-free, pigmented and pre-filled coating material based on a dual-component, light and weather resistant polyurethane resin.
<b>Usage area:</b>	Inside and outside areas: balconies, terraces, exhibition pergolas areas behind windows
<b>Usage:</b>	<ul style="list-style-type: none"><li>• Layer thickness between 1.3 mm und 3 mm</li><li>• For better protection from abrasion and scratching, we advise to use our Products GI 613 an GI 614 as sealant for areas, which when using, should keep the intended design and look.</li></ul>
<b>Properties:</b>	<ul style="list-style-type: none"><li>• Slight to medium mechanical and chemical stress</li><li>• High flexibility</li><li>• Usable in permanently wet areas</li><li>• Easy to clean</li><li>• Smooth coating, but with the addition of special fillers, antiskid coatings can be made dependent on the requirements of respective trade associations.</li></ul>
<b>Substrate:</b>	<ul style="list-style-type: none"><li>• Priming mandatory: Dependent on substrate GI 110 or GI 115, for mastic asphalt substrates GI 210 or GI 215 can be used.</li></ul>

### Technical Data:

<b>Colour:</b>	RAL 7032; more colours on request
<b>Package size:</b>	30 kg; other units on request
<b>Storage life:</b>	From production date 12 months; store in original containers; dry, cool, frost free
<b>Density at 23°C / 50 % air humidity: EN ISO 2811-2:2011</b>	Approx. 1.44 g/cm <sup>3</sup>
<b>Shore hardness: ISO 7619-1:2012</b>	A > 75
<b>Solid parts:</b>	Approx. 100 %
<b>Viscosity (25°C, V03.4): EN ISO 2884-1:2006</b>	Component A: 2100 – 3400 mPas Component B: 900 – 1400 mPas
<b>Mixing ratio:</b>	4 : 1 (by weight) 3.1 : 1 (by volume)
<b>UV-resistance:</b>	A slight colour change and chalking is expected.
<b>Chemical resistance:</b>	When completely cured resistant against: Water, sea and waste water, a number of brines, diluted acids, saline solutions, mineral oils, lubricants, fuels and many solvents (some materials a change in colour is possible). We advise to do some testing yourself depending the intended use.

## Processing data:

<b>Material usage:</b>	1.5 kg/m <sup>2</sup> /mm layer thickness Minimum layer thickness: 1.3 mm Recommendation: 2.0 – 2.5 kg/m <sup>2</sup> These values are dependent on how the product is processed and on the substrate. The values are therefore only for a rough estimate.
<b>Processing time (50 % air humidity):</b>	15 – 20 minutes (30 °C) 30 – 40 minutes (20 °C) 60 – 80 minutes (10 °C)
<b>Revision time: (50 % air humidity):</b>	Min. 6 - 8 hours, max. 12 hours at 30 °C Min. 12 - 16 hours, max. 24 hours at 20 °C Min. 24 - 36 hours, max. 48 hours at 10 °C
<b>Curing time (complete mechanical stress at 50 % air humidity):</b>	3 days (30 °C) 7 day (20 °C) 10 days (10 °C)
<b>Processing temperature:</b>	10 – 30 °C

## Processing:

### Preparation of the substrate:

- Substrate must be dry, clean, rough, stable and free of separating substances like oil, fats etc.
- Coating takes place on a prepared and primed substrate.
- Within the revision time, the coating can be applied directly onto the prepared and primed substrate. If the revision time is exceeded, the surface must be broadcasted with fire-dried Quartz-sand or, otherwise this area must be prepared by grinding after curing for the next layer.

### Tools:

- Trowel, triangular toothed blades or similar

### Mixing:

- Pour the curing agent completely into the resin compound.
- Mix intensively with slow turning mixer (we advise a double-stirrer with the stirring units turning the opposite direction to each other).
- Fill into another vessel and mix again.
- Before applying to the substrate make sure to have an even and smear-free mixture.
- It is not advised to fill up with quartz sand.

### Application:

- The product is to be poured onto the prepared area and evenly spread across the surface with a scraper preferably with triangular toothed blades.
- If necessary deaeration can be made by use of a spiked roller. In case of perturbations arising from the substrate the coating indeed has to be deaerated.
- In case of bigger areas care must be taken to work on in time in order to minimize overlapping traces and colour differences.

### Processing conditions:

- The material, air and ground temperature must be between 10 °C and 30°C during the processing, installation and curing time.
- The substrate temperature must be at least 3 °C above the dew point.
- The air humidity should not be above 80% at any time. The application should take place when temperature is at a constant or falling value to avoid blisters because of the extension of air underneath the ground. It is important to keep an eye on the venting during and after the application. The area must be protected from any direct water contact during the whole curing time.

**Further information:**

<b>CE label:</b>	DIN EN 13813: 2002
<b>Safe handling:</b>	The product is intended for professional use. Leaflet M044, production and processing of Polyurethanes and isocyanates. Please note the current safety data sheets.
<b>VOC-contents:</b>	VOC-directive 2004/42/EG: Category IIA/j type Ib < 500 g/l VOC
<b>Disposal:</b>	Disposal with the assistance of a disposal specialist under consideration of the current safety data sheets.
<b>GISCODE:</b>	PU 40

**Data base:**

The determination of all the data and application information is based in laboratory tests. Measured values in practice may differ because of influences beyond our control.

**Legal foundation:**

The following specifications as well as the recommendations for handling and use of our products are based upon our knowledge and experience under normal conditions, at proper storing and application. Because of different materials, substrates and working conditions other than given normal values, a warranty of a working result or a liability – for whatever legal relationship - cannot be justified from these instructions or a verbal guidance respectively, unless intent or gross fault can be imputed to us. Here, the user has to prove that he had transferred in written form, in time and completely every knowledge that is necessary for an appropriate and promising estimation. The user is obliged to test the products on their suitability for the intended purpose. Incidentally our respective terms and conditions of business are valid. You get these on [www.gremmler.de](http://www.gremmler.de). Only the newest edition of this technical data sheet is valid.

**GREMMLER BAUCHEMIE GMBH  
LISE-MEITNER-STRASSE 5  
46569 HÜNXE**

**Phone: +49 (0)281 9440340**

**FAX: +49 (0)281 9440344**

**[info@gremmler.de](mailto:info@gremmler.de)**

**[www.gremmler.de](http://www.gremmler.de)**